



אלמור פיברגלס יבוא יצוא 1996 בע"מ

Product Information

▶ **AEROSIL® 200** **Hydrophilic Fumed Silica**

AEROSIL® 200 is a hydrophilic fumed silica with a specific surface area of 200 m²/g.

Applications and Properties

Applications

- Paints and coatings
- Unsaturated polyester resins, laminating resins and gel coats
- HTV- and RTV-2K-silicone rubber
- Adhesives and sealants
- Printing inks
- Cable compounds and cable gels
- Plant protection
- Food and cosmetics

Properties

- Rheology and thixotropy control of liquid systems, binders, polymers, etc.
- Used as anti-settling, thickening and anti-sagging agent
- Reinforcement of HTV- and RTV-2K-silicone rubber
- Improvement of free flow and anticaking characteristics of powders

Physico-chemical Data

Properties	Unit	Typical Value
Specific surface area (BET)	m ² /g	200 ± 25
Average primary particle size	nm	12
Tapped density* (approx. value) acc. to DIN EN ISO 787/11, Aug. 1983	g/l	approx. 50
Moisture * 2 hours at 105 °C	wt. %	≤ 1.5
Ignition loss, 2 hours at 1000 °C, based on material dried for 2 hours at 105 °C	wt. %	≤ 1.0
pH in 4% dispersion		3.7 - 4.7
SiO ₂ -content based on ignited material	wt. %	≥ 99.8

* ex plant

The data represents typical values and not production parameters.

AEROSIL®



Safety and Handling

With every sample or initial shipment of our products we will send a Material Safety Data Sheet. Of course you can also ask at any time for a MSDS or any other information regarding product safety.

Packaging and Storage

AEROSIL® 200 is supplied in multiple layer 10 kg bags. We recommend to store the product in closed containers under dry conditions and to protect the material from volatile substances. AEROSIL® 200 should be used within 2 years after production.

Registration

	CAS-No.	EINECS	TSCA (USA) AICS (Australia), CEPA (Canada)	MITI (Japan)	ECL (Korea)	NEPA (China)
AEROSIL® 200	112 945-52-5 7631-86-9	231-545-4	Registered	1-548	KE-30953 (KE-31032)	List 1

► For further information please contact:

Commercial Contact

Degussa AG

Business Line Aerosil
Weissfrauenstrasse 9
D-60287 Frankfurt am Main,
Germany
Phone: +49 69/218-2532
Fax: +49 69/218-2533
E-Mail: aerosil@degussa.com
http://www.aerosil.com

NAFTA

Degussa Corporation

Business Line Aerosil
379 Interpace Parkway,
P.O. Box 677
Parsippany, NJ 07054-0677
Phone: +1 (800) AEROSIL
Phone: +1 (973) 541-8510
Fax: +1 (973) 541-8501

Asia (without Japan)

Aerosil Asia Marketing Office

c/o NIPPON AEROSIL CO., LTD.
P.O. Box 7015
Shinjuku Monolith 13F
3-1, Nishi-Shinjuku 2-chome
Shinjuku-ku, Tokyo
163-0913 Japan
Phone: +81-3-3342-1786
Fax: +81-3-3342-1761

Japan

NIPPON AEROSIL CO., LTD.

Sales & Marketing Division
P.O. Box 7015
Shinjuku Monolith 13F
3-1, Nishi-Shinjuku 2-chome
Shinjuku-ku, Tokyo
163-0913 Japan
Phone: +81-3-3342-1763
Fax: +81-3-3342-1772

Technical Contact

Degussa AG

Technical Service Aerosil
Rodenbacher Chaussee 4
P.O. Box 1345
D-63403 Hanau-Wolfgang,
Germany
Phone: +49 6181/59-3936
Fax: +49 6181/59-4489

NAFTA

Degussa Corporation

Technical Service Aerosil
2 Turner Place
Piscataway, NJ 08855-0365
Phone: +1 (888) SILICAS
Phone: +1 (732) 981-5000
Fax: +1 (732) 981-5275

Asia (without Japan)

Degussa AG

Technical Service Aerosil
Rodenbacher Chaussee 4
P.O. Box 1345
D-63403 Hanau-Wolfgang,
Germany
Phone: +49 6181/59-3936
Fax: +49 6181/59-4489

Japan

NIPPON AEROSIL CO., LTD.

Applied Technology Service
3 Mita-cho
Yokkaichi, Mie
510-0841 Japan
Phone: +81-593-45-5270
Fax: +81-593-46-4657

Or your local Degussa Representative

The information in this document is based on our best knowledge. We disclaim any warranty and liability whatsoever as to accuracy and completeness of such information as well as to the potential infringement of any proprietary rights. We reserve the right to effect technical alterations. Any user of our products shall bear the full risk connected to their use including but not limited to their properties and fitness for any purpose.